

In the Specification*On page 19, please replace Table 1 with the following:*

	Content of element in iron powder (% by mass)						Degree of precipitation of S compound	Application of finish reduction	First-order rate constant of dehalogenation of TCE (hr ⁻¹)
	S	Mn	C	Si	P	O			
Comparative Example [1] 3	0.03	0.05	0.05	0.08	0.03	0.90	20	No	0.01
Example 2	0.1	0.06	0.05	0.08	0.03	0.70	30	No	[0.01] 0.08
Example 3	0.20	0.09	0.005	0.08	0.15	0.70	20	No	0.06
Example 4	0.4	0.05	0.005	0.08	0.03	0.05	20	Yes	0.07
Example 5	0.94	0.04	0.005	0.08	0.01	0.05	30	Yes	0.09
Example 6	0.10	0.05	0.05	0.08	0.01	0.05	10	Yes	0.04
Comparative Example 7	0.20	0.40	0.10	0.08	0.03	0.60	0	No	0.01
Comparative Example 8	0.20	0.40	0.005	0.08	0.04	0.05	0	Yes	0.02
Comparative example 1	0.014	0.05	0.15	0.08	0.016	0.90	0	No	0.001
Comparative Example 2	0.014	0.05	0.005	0.08	0.016	0.05	0	Yes	0.005